

PCF28

MATERIAL	PCF28 is a PTFE compounded material with carbonfiber and graphite additives.
DESCRIPTION	The additives are for oil or water lubricated and unlubricated applications. It has very good wear, extrusion, chemical and abrasion resistance. However it has medium low friction. It also has very good dry running properties.
APPLICATION	oil or water (un)lubricated applications.
TEMPERATURE	The temperature range is between -200°C and 260 °C

Maximum and minimum working temperature is depending on the specific application criteria

PHYSICAL PROPERTIES	TEST METHOD	UNIT	VALUE
Color			Dark grey
Specific gravity	ASTMD792 at 23°C	g/cm ³	2,08
Hardness	ASTMD2240 at 23 °C	Shore D	58
Tensile strength at break	ASTMD4894 at 23 °C	Mpa	22,8
Elongation at break	ASTMD4894 at 23 °C	%	278
Service temperature range	/	°C	-200/260

The above values are typical

The information in this datasheet is based on many years of experience in the application of PCF28. However, unknown parameters and conditions may restrict general statements during usage. It is vital that users satisfy themselves as to the suitability of individual products through adequate testing. For this reason and due to the wide range of applications of our products, AST B.V. can accept no liability as to the suitability or correctness of our recommendations in individual cases. The application limits for pressure, temperature and velocity given in this datasheet are maximum values determined in the test laboratory. During practical applications it should be remembered that due to the interaction of the operating parameters, the maximum values must be set correspondingly lower. For exceptional operating conditions, please contact us.